

Bergendal Blend Satin FBS




CLASSIFICATION

FBS

TEXTURE

Bricks with a flat and even surface, providing a clean look with minimal texture.

Choose clay face bricks for their unmatched durability, timeless beauty, and excellent thermal insulation, all while requiring no maintenance, ensuring your building stands the test of time with minimal effort.



Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

Bergendal Blend Satin FBS



SPECIFICATIONS

Size (width x length x height)	225 x 108 x 75mm	Classification	FBS
SANS	227:2007	ISO	9001:2015
Typical Compressive Strength	>27 MPa	Typical 24 ^{hr} Water Absorbtion	>9%
Moisture Expansion Category	II	Efflorescence Rating	Nil
Expoure Zone Suitability	1-2	Bricks per m ² (excluding cutting & waste)	51
Factory Manufactured At	Middelwit	Bricks per pallet	500
Average mass per brick	2.7kg	Available in Special Shaped Bricks	No



www.corobrik.co.za



Download the high-resolution swatches, BIM files and view more project photos | www.corobrik.co.za

Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

For image and project credits, please visit: www.corobrik.co.za/featured-projects

Information correct as at 28/06/2024