


Redwood Travertine FBS



CLASSIFICATION	FBS
TEXTURE	A light textured finish with a natural clay grain appearance.

Choose clay face bricks for their unmatched durability, timeless beauty, and excellent thermal insulation, all while requiring no maintenance, ensuring your building stands the test of time with minimal effort.




Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.

Redwood Travertine FBS




SPECIFICATIONS

Size (length x width x height)	222 x 106 x 73mm	Classification	FBS
SANS	227:2007	ISO	'-
Typical Compressive Strength	>20 MPa	Typical 24 ^{hr} Water Absorbtion	>8%
Moisture Expansion Category	III	Efflorescence Rating	Nil
Expoure Zone Suitability	02-Jan	Bricks per m ² (excluding cutting & waste)	51
Factory Manufactured At	Rosema, Gauteng	Bricks per pallet	480
Average mass per brick	2.6kg	Available in Special Shaped Bricks	Yes



www.corobrik.co.za



Download the high-resolution swatches, BIM files and view more project photos | www.corobrik.co.za