
Buff Satin FBS





Buff Satin FBS



SPECIFICATIONS

Size (width x length x height)	222 x 106 x 73mm	Classification	FBS
SANS	227:2007	ISO	<i>i_</i>
Typical Compressive Strength	>25 MPa	Typical 24hr Water Absorbtion	>10%
Moisture Expansion Category	I	Efflorescence Rating	Nil
Expoure Zone Suitability	1-2	Bricks per m² (excluding cutting & waste)	51
Factory Manufactured At	Rosema, Gauteng	Bricks per pallet	480
Average mass per brick	2.6kg	Available in Special Shaped Bricks	Yes



www.corobrik.co.za

Download the high-resolution swatches, BIM files and view more project photos |

Variations in colour, texture, and size are natural characteristics of clay products and production variations can occur from batch to batch. Whilst every effort is made to provide brochures consistent with products delivered to site, they should be viewed as a guide only.